IN THE CLAIMS

Claims 1-11) Previously canceled.

- 12) (currently amended) A flexible superconducting core for a superconducting power cable, said core comprising:
 - a) a helical [externally] <u>central</u> corrugated flexible tubular element [comprised] <u>made</u> of stainless steel;
 - b) a stainless steel core mesh positioned around [said] a helical central corrugated flexible [central core] tubular element to provide a relatively flat surface, said mesh consisting of:
 - i) a first layer of steel tape of one size; and
- ii) a second layer of steel tape having a different said size from said first layer
 of said steel tape, said [first] second layer being positioned over said [second] first layer;
 - c) a layer of at least one copper tape, positioned on top of said second layer of said steel tape;
 - d) a plurality of superconducting tapes layered over said at least one said copper tape, forming a first group of a plurality of superconducting tape layers;
 - e) a second group of a plurality of superconducting tape layers, at least one said layer of said second group positioned on top of said first group of plurality of
 - [suberconducting] <u>superconducting</u> tapes being wound in one direction opposite that of (d); and
 - wherein a pitch of all the layers varies from a maximum P_{max1} [(1000 cm)] and P_{max2} [(1000 cm) in the intermediate] medium layers to minimum [and a] P_{min1} [2 cm)] and

 P_{min2} [2 cm) in the external] in inner and outer layers layers, while [a] twist angles of the tapes in [all of] the layers [varies] vary from α_{max1} [(45 degrees)) to α_{min1} [(0 degrees)] and from $[\alpha_{max2}$ (45 degrees)] $\underline{\alpha}_{max1}$ to α_{min2} [(0 degrees) in at least one of the layers of tapes placed between the external surface of the core and [the] an internal part of the layer, being the current distribution between the layers uniform and each cable layer operating at total current conductance] and at least one layer of tapes from normally conducting metal is located between the outer surface of the former and the inner surface of said layer,

wherein:

a) for inner layers:

i) P_{min1} and α_{max1} is defined as minimum pitch and maximum twist angle of said tapes in the first layer made of superconducting tapes from the cable axis:

ii) P_{mez1} and α_{min1} is defined as maximum pitch and minimum twist angle of said tapes, the last layer from the cable axis layer made of superconducting tapes of the part of layers adjacent to the former and having one direction of lay; and

b) for outer layers:

 P_{min2} and α_{max2} is defined as minimum pitch and maximum twist angle of tapes in the first layer made of superconducting tapes from the cable axis; and

 P_{max2} and α_{min2} is defined as maximum pitch and minimum twist angle of tapes in the first layer from the cable axis layer made of superconducting tapes of the second part of layers with opposite direction of lay.

- 13) (currently amended) The flexible [conductor] <u>superconducting</u> core according to claim [1] <u>12</u>, wherein said flexible tubular <u>corrugated</u> element has an external diameter of preferably between 4 and 6 cm, an internal diameter between 2 and 4 cm, a corrugation depth ranging between 0.5 cm and 1 cm, and a corrugation pitch between [1.6 and 3] <u>0.8 and 1.5</u> cm.
- 14) (currently amended) The flexible [conductor] <u>superconducting</u> core for claim [1] <u>12</u>, wherein the stainless steel tape for said first layer has a width <u>ranging</u> between 4 cm and 5 cm and a thickness between 0.005 to 0.006 cm and spacing ranging from 0.15 to 0.2 cm and the second layer of stainless steel tape is applied which has a width ranging from 2.5 to 4 cm and a thickness ranging from 0.001 to 0.002 cm with a spacing ranging from 0.1 to 0.15 cm.
- 15) (currently amended) The flexible [conductor] superconducting core [for a superconducting power cable] according to claim 1, wherein the [tubular element consists of a] first layer of copper tapes [with] has a width ranging from 0.25 cm to [4.0] .40 cm and a thickness ranging from 0.025 to 0.030 cm with a laying length ranging from 2 to 100 cm.
- 16) (currently amended) The flexible [conductor] <u>superconducting</u> core [for a superconducting power cable] according to claim [1] <u>12</u>, wherein said core operates with a current selected from the group consisting of direct current, alternate current, current pulses and combinations thereof.
 - 17) (currently amended) The flexible [conductor] superconducting core [for a

superconducting power cable] according to claim 1, wherein said [superconducting] tapes of copper are made from the group consisting of metals and alloys with low electric resistance based on a metal selected from the group consisting of aluminum, copper and silver.

- 18) (previously canceled)
- 19) (cancel)
- 20) (previously amended) The [flexible conductor] <u>superconducting</u> core [for superconducting power cable] according to claim 1, wherein said superconducting elements of the flexible conductor core to be used may be a shape selected from the group consisting of flat, round oval and a sector.